

PATENTED



THERMO-SNAP™

by Benchmark Foam

Achieve **R-10** for sub-slab and in-floor heat systems

Thermo-Snap™ insulated panels:

The traditional method of installing in-floor heat was time-consuming and costly for contractors and homeowners.

Patented **Thermo-Snap™** panels reduce labor and material costs with a tube management system built in to the EPS (expanded polystyrene) insulated panel.

- Pex tubes snap into manufactured pathways
- Tubes remain in place during concrete pour - no float or displacement
- Minimal staple usage means savings
- Quick, easy tube installation cuts labor costs
- Predetermined tube placement ensures even spacing and heating
- Accurate tube placement provides quick, professional appearance
- Easily trimmed to accommodate custom shapes
- Retains strong bond with concrete
- Acts as a stable thermal barrier to reduce heat loss
- Qualifies for green building programs, such as LEED



Specifications:

- 2.5" thick, 4' x 4' standard panels with 1/2" or 5/8" tube pathways on 6" centers
- Can customize to specific panel and tube sizes
- Manufactured with certified EPS
- Meets code requirements of R-10 and above

See reverse for technical data.



Thermo-Snap™ Technical Data

Property	Units	ASTM Test	Values Meet or Exceed ASTM C578		
Density, min.	lbs/ft ³	C303 or D1622	1.25	1.80	
Thermal Resistance "R Value"	2.5 inches thick	C177 or C518	@ 40° F @ 75° F*	11.0 10.1	11.8 10.8
Strength Properties, minimum					
Compressive (@ 10% deformation)	psi	D1621	16.0	25.0	
Flexural	psi	C203	30	50	
Moisture Resistance					
Water Absorption (by total immersion, max.)	vol %	C272	3.0	<2.0	
Water Vapor (Permeance, max.)	Perms	E96	3.5	2.5	
Oxygen index, min.	vol %	D696	24.0	24.0	
Flame Spread @ 6"		UL® (BRYX)	20	20	
Smoke Development		UL® (BRYX)	300	300	

All values are based on data from Flint Hills Resources, NOVA Chemical Company and BASF Corporation.

*Federal Trade Commission ruling: Use the 75° R-Value when calculating R-Values for residential construction (fact sheet available upon request).

DESIGN CONSIDERATIONS:

Flammability: Like many construction materials, expanded polystyrene (EPS) is combustible. It should not be exposed to flame or other ignition sources. Current building code requirements should be met for adequate protection or separation from occupied areas.

Solvent Exposure: EPS is subject to attack by petroleum-based solvents and adhesives, and coal tar pitch products. Care should be taken to prevent EPS direct contact with these products and their vapors. Use only adhesives approved for EPS applications.

Visit us online at
www.BenchmarkFoam.com

Call today for an estimate on your current project!
 605-886-8084 or 800-658-3444

*Benchmark Foam knows that your business depends on our product arriving on time. Our service response is so dependable we back it with Benchmark Foam's **On-Time Guarantee**. Your product will be shipped and arrive by the agreed-to arrival date or we will **discount your invoice 10 percent**. We work to accommodate customer needs, giving you confidence when you place an order, even if it needs to be rushed. And we do not have truckload quotas, so no matter how large or small, your order will be shipped on time.*

401 Pheasant Ridge Drive • Watertown, SD 57201 • Phone: 605-886-8084 • Toll Free: 800-658-3444 • Fax: 605-886-8099 • www.BenchmarkFoam.com

Quick response is our guarantee.